



# BASYPOL 115

Chrome Basifying Agent

<b>Chemical composition</b>	Blend of Organic and Inorganic compounds
<b>Activity</b>	98%
<b>Appearance</b>	White powder
<b>Solubility</b>	Sparingly soluble in weak acid solutions
<b>Shelf life</b>	Up to 1 year at temperatures between 5 and 40° C.
<b>Dilution</b>	Added Undiluted

## Field of application

For the basification of chrome in chrome tanning.

## Properties

BASYPOL 115 being blend of special Inorganic compounds is an effective basifying agent .

BASYPOL 115 provides Wet Blue with uniform pleasant colour.

Avoids lot to lot variation of colour.

Provides smooth tight grain.

BASYPOL 115 provides maximum exhaustion and basification of chrome.

BASYPOL 115 increases the pH of the bath gradually and consistantly as the product is manufactured in such a way that it makes sustained rate of release of its compound when used .

BASYPOL 115 eliminates the chances of looseness and avoids over basification.

## Application:

BASYPOL 115 is applied after through and through penetration of chrome and after the running time of Basic Chromium Sulfate.

BASYPOL 115 is added undiluted.

## Quantities:

Depending upon end pickle pH requirement a dosage of 0.3% to 0.5% will be enough.

To achieve pH 4.0 it is adviced to run 5 to 6 hours.

his information and our technical advice - whether verbal, in writing or by way of trials - are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to check its validity and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with our General Conditions of Sale and Delivery.

**ZSIVIRA CHEMIE MERIK PRIVATE LIMITED**

10/10