



ZEOPALIN XLS

Degreasing Agent

Chemical composition	Blend of Fatty Alcohol Ethoxylates
Appearance	Clear Transparent Liquid
Charge	Nonionic
In Stability to electrolytes	Stable to acids and salts
Shelf life	Up to 1 year at temperatures between 5 and 40° C.

Field of application

Degreasing of all kinds of leathers .

Properties

Excellent degreasing properties for all types of leather.

Improves the levelness of the dyeing.

Opens up fibres and facilitates penetration of other tanning auxiliaries.

Free from APEO. Fully BIODEGRADABLE.

Application:

The Degreasing with ZEOPALIN XLS is best without any float. Bated Pelts are degreased after fleshing. Pickled pelts are warmed up prior to degreasing at 35°C.

The pelts are drummed for 60 – 90 minutes without float with the necessary quantities. The dissolved and emulsified fat is removed by souring in 200 to 300% water at 35°C.

In order to avoid acid swelling pickled pelts have to be washed thoroughly.

Quantities:

Bated Sheep :	1.0 - 6.0 %
Bated Lamb :	2.0 - 6.0%
Pickled Goat :	1.0 – 5.0%
Pickled Sheep :	2.0 to 7.0%
Chrome tanned split In Soaking/Liming	0.5 to 4.0% upto 0.5%

Note : The product being combination of various raw materials, there are Chances of variations in colour , odour and viscosity.

The property and Application of the product will remain same.

This information and our technical advice - whether verbal, in writing or by way of trials - are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to check its validity and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with our General Conditions of Sale and Delivery.

ZSIVIRA CHEMIE MERK PRIVATE LIMITED

11/13