



# ZSIVIROL FS*i*

Sulfited Fish Oil

<b>Chemical composition</b>	Oxidised & Sulfited fish oil with synthetic oils and emulsifiers
<b>Fattening substance</b>	60 %
<b>Appearance</b>	Reddish Brown oil
<b>pH - value 1 : 10</b>	5.5 – 7.0
<b>Charge</b>	Anionic
<b>In Stability to electrolytes</b>	Stable to acids and salts under usual tannery conditions. Stable to Chrome
<b>Shelf life</b>	Up to 1 year at temperatures between 5 and 40° C.
<b>Dilution</b>	Combinations with other fatliquors have to be stirred thoroughly before dilution. dilution method: 1 : 3 with water of 50 - 60° C.

## Field of application

Fatliquor for soft garment , goods and upholstery leathers

## Properties

Provides leather with good softness and soft touch.

Provides excellent inner softness.

Fair Light Fastness.

Compatible with other fatliquors.

## Application:

**ZSIVIROL FS i** is used in chrome tanning , retanning and main fatliquoring.

## Quantities:

In chrome tanning 0.5 - 2,0 % ZSIVIROL FS*i*

In chrome retanning: 1.0 - 2.0% ZSIVIROL FS*i*

In main fatliquor for garment  
Goods & upholstery leathers 3.0 – 6.0% ZSIVIROL FS*i*

This information and our technical advice - whether verbal, in writing or by way of trials - are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to check its validity and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with our General Conditions of Sale and Delivery.

**ZSIVIRA CHEMIA MERK PRIVATE LIMITED**

02/12