



ZSIVIROL RC 33

Synthetic Oil with softeners

Chemical composition	Blend of Synthetic Oil and softeners
Fattening substance	55 ± 2%
Appearance	Pale Brown to Red oil
pH - value 1 : 10	5.5 – 7.0
Charge	Anionic
Stability to electrolytes	Stable to acids and salts under usual tannery conditions. Stable in chrome liquors
Shelf life	Up to 1 year at temperatures between 5 and 40° C.
Dilution	Combinations with other fatliquors have to be stirred thoroughly before dilution. dilution method: 1 : 3 with water of 50 - 60° C.

Field of application

Fatliquor for very soft, lightfast and odourless leathers.

Properties

ZSIVIROL RC 33 gives excellent inner softness to the leather.

Good light fastness

Provides Fullness and smooth touch

Best for light weight leathers.

Application:

ZSIVIROL RC 33 is mainly used for nappa and gloving where pronounced inner softness and smooth touch is required ..

Quantities:

Garment leather : Upto 7 %

Glove leather: 5.0% to 8%

Upholstery : Upto 8%

Note : The product being combination of various raw materials, there are Chances of variations in colour and viscosity. The property and Application of the product will remain same.

This information and our technical advice - whether verbal, in writing or by way of trials - are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to check its validity and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with our General Conditions of Sale and Delivery.

ZSIVIRA CHEMIE MERK PRIVATE LIMITED

03/13