



ZSIVITAN ARE

Acrylic polymer with Dispersants

Chemical composition	Blend of Polyacrylate with Dispersants
Solids	Approx 30%
Appearance	White to Pale white viscous liquid
pH - value 1 : 10	5.5 – 6.5
Charge	Anionic
Shelf life	Up to 1 year at temperatures between 5 and 40° C.
Dilution	Added Undiluted

Field of application

Anionic retanning agent for all kinds of leather chrome tanned, semi-chrome and full vegetable leather.

Properties

ZSIVITAN ARE is suitable for filling and tightening all types of chrome leathers
Allow even dyeing with brilliant shades.
Enables other syntans to penetrate well into the fibres

Application:

ZSIVITAN ARE is applied alone or along with vegetable and/or synthetic tannins.

Quantities:

In the Softy & Upper leather: 3 to 4 % ZSIVITAN ARE

Garment leather: 3 to 5% ZSIVITAN ARE

Note:

AS THE PRODUCT IS THE COMBINATION OF MANY RAW MATERIALS, THE COLOUR AND VISCOSITY OF THE PRODUCT MAY SLIGHTLY VARY FROM TIME TO TIME. BUT THE TECHNICAL ASPECT OF THE PRODUCT WILL REMAIN SAME AT ALL TIMES.

The information in this leaflet and our technical advice - whether verbal, in writing or by way of trials - are given in good faith but without warranty. and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to check its validity and to test our products as to their suitability for the intended processes and uses. The application and use of our products in your production system even though it is on the basis of our technical advice are beyond our control as the raw material you use may vary from time to time and, therefore, our products are used entirely under your own responsibility. Our products are in accordance with our General Conditions of Sale and Delivery.

ZSIVIRA CHEMIE MERK PVT LIMITED