



ZSIVITAN 2PW

Replacement Syntan

Chemical composition	Phenol condensation product
Activity	ca. 95%
Appearance	Light tan powder
pH - value 1 : 10	5.0 – 6.0
Charge	anionic
Shelf life	Up to 1 year at temperatures between 5 and 40° C.
Dilution	Added Undiluted

Field of application

In the retanning of neutralised leather.

Properties

Gives a soft leather with a full handle and a fine grain.

Good filling properties

Allows an even dyeing without patch.

Application:

ZSIVITAN 2PW is applied on neutralized leathers alone or along with other syntans or vegetable tannins.

Quantities:

In the Softy leather: 3 to 6 % ZSIVITAN 2PW

Corrected grain leather: 3% to 4% ZSIVITAN 2PW

Garment leather: 3% to 5% ZSIVITAN 2PW

AS THE PRODUCT IS THE COMBINATION OF MANY RAW MATERIALS, THE COLOUR OF THE PRODUCT MAY SLIGHTLY VARY FROM TIME TO TIME. BUT THE TECHNICAL ASPECT OF THE PRODUCT WILL REMAIN SAME AT ALL TIMES.

This information and our technical advice - whether verbal, in writing or by way of trials - are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to check its validity and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with our General Conditions of Sale and Delivery.

ZSIVIRA CHEMIE MERK PRIVATE LIMITED

01/09