



ZSIVITAN ALM

Aluminium Tanning Agent

Chemical composition	Cationic Aluminium Salts
Aluminium Oxide content	13 - 16 %
Basicity	50 – 55%
pH - value 1 : 10	1 – 3
Charge	Cationic
Appearance	Pale White Powder
Shelf life	Up to 6 months at temperatures between 5 and 40° C.
Dilution	Added to drum directly

Field of application

In the wet white tanning, chrome free tanning and chrome retanning, in the EI / Vegetable tanning , solo aluminium and semi aluminium tanning.

Properties

ZSIVITAN ALM provides soft, smooth leather with tight and firm grain. ZSIVITAN ALM has good filling effect. ZSIVITAN ALM due to its cationic action makes dyesuffs penetrate well into the leather and also makes dyeing surface evenly dyed with high light fastness.

Quantities:

In the Tanning (after Chrome tanning) :1 to 2.5% (on pelt weight)

In Goatskin Suede, Nubuck and Shoe Upper : 2 to 5%

Retanning of Vegetable tanned leather

EI sheep and goat skins : 8 to 12%

Note:

AS THE PRODUCT IS THE COMBINATION OF MANY RAW MATERIALS, THE COLOUR OF THE PRODUCT MAY SLIGHTLY VARY FROM TIME TO TIME. BUT THE TECHNICAL ASPECT OF THE PRODUCT WILL REMAIN SAME AT ALL TIMES.

The information in this leaflet and our technical advice - whether verbal, in writing or by way of trials - are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to check its validity and to test our products as to their suitability for the intended processes and uses. The application and use of our products in your production system eventhough it is on the basis of our technical advice are beyond our control as the raw material you use may vary from time to time and, therefore, our products are used entirely under your own responsibility. Our products are in accordance with our General Conditions of Sale and Delivery.

ZSIVIRA CHEMIE MERK PRIVATE LIMITED