

# ZSIVIRA

### **ZSIVIROL BAZ**

Chemical composition	Modified lecithin with esters
Active Solids	45% +/-2%
Appearance	Pale Beige paste
pH - value 1:10	$5.\theta-6.\theta$
Charge	Nonionic
Stability to electrolytes	Highly stable to acids and salts under usual tannery conditions. Stable in chrome liquors.
Shelf life	Up to 1 year at temperatures between 5 and 40° C.
Dilution	Combinations with other fatliquors have to be stirred thoroughly before dilution. dilution method: $1:3$ with water of $50-60^\circ$ C.

#### **Properties and Application:**

- > Excellent softness without looseness.
- Doesnot bleach the colour. Allows brilliant shade dyeing.
- > Very good light fastness.
- Provides permanent softness with bounciness even in prolonged storage.
- ➤ Will not load the leather and hence Produces light weight leathers.
- Improves penetration of other fatliquors and produces leather without greasiness.

The above information on application on leather is given in accordance to the best of our knowledge and our lab applications. As the usage of the product by the consumer is not under our control, we are not liable for any sort of claims or reimbursements. The product is given without any guarantee/warranty in connection to end use.



# ZSIVIRA

## **ZSIVIROL BAZ**

#### **Usage Quantities:**

Nappa Upper leather: upto 7% ZSIVIROL BAZ

Glove leather: upto 5% ZSIVIROL BAZ

Garment leather: 3% to 7% ZSIVIROL BAZ

uphostery leather: upto 8 % ZSIVIROL BAZ

Due to Purest form of Lecithin used, a thin dark brown layer will be formed on the product surface when stored in drums which will disperse on stirring. This has no influence on the shelf life or performance of the product.

Note: The product being combination of various raw materials, there are Chances of variations in colour and viscosity. The property and Application of the product will remain same.

The above information on application on leather is given in accordance to the best of our knowledge and our lab applications. As the usage of the product by the consumer is not under our control, we are not liable for any sort of claims or reimbursements. The product is given without any guarantee/warranty in connection to end use.