

ZSIVIRA

ZSIVIROL FB2A

Chemical composition	Oxidised & Sulfited fish oil with dispersants and emulsifiers
Solids	60 %
Appearance	Reddish Brown oil
pH - value 1:10	5.5 - 6.5
Charge	Anionic
In Stability to electrolytes	Stable to acids and salts under usual tannery conditions. Stable to Chrome
Shelf life	Up to 1 year at temperatures between 5 and 40° C.
Dilution	Combinations with other fatliquors have to be stirred thoroughly before dilution. dilution method: $1:3$ with water of $50-60^{\circ}$ C.

Field of application:

Fatliquor for soft garment, goods and upholstery leathers

Properties and Application:

- > Provides leather with good softness and soft touch.
- > Provides excellent inner softness.
- > Fair Light Fastness.
- Compatible with other fatliquors.
- Can be used in chrome tanning, retanning and main fatliquoring.

The above information on application on leather is given in accordance to the best of our knowledge and our lab applications. As the usage of the product by the consumer is not under our control, we are not liable for any sort of claims or reimbursements. The product is given without any guarantee/warranty in connection to end use.



ZSIVIRA

ZSIVIROL FB2A

Usage Quantities:

In chrome retanning: 1.0 - 2.0% ZSIVIROL FB2A

In main fatliquor for garment Goods & upholstery leathers

3.0 - 8.0% ZSIVIROL FB2A

Note: The product being combination of various raw materials, there are Chances of variations in colour and viscosity. The property and Application of the product will remain same.

The above information on application on leather is given in accordance to the best of our knowledge and our lab applications. As the usage of the product by the consumer is not under our control, we are not liable for any sort of claims or reimbursements. The product is given without any guarantee/warranty in connection to end use.