

# ZSIVIRA

## **ZSIVIROL IC2N**

Chemical composition	Blend of Synthetic Oils
Active Solids	55 to 60 %
Appearance	Brown oil to semi viscous fluid
pH - value 1:10	$5.\theta-6.\theta$
Charge	Anionic
Stability to electrolytes	Stable to acids and salts under usual tannery conditions. Stable in chrome liquors
Shelf life	Up to 1 year at temperatures between 5 and 40° C.
Dilution	Combinations with other fatliquors have to be stirred thoroughly before dilution. dilution method: $1:3$ with water of $50-60^{\circ}$ C.

#### Field of application:

ZSIVIROL IC2N is mainly used for high quality leather as gloving and garment in the main fatliquoring bath.

Fatliquor for soft, lightfast and odourless leathers.

#### **Properties and Application:**

- > ZSIVIROL IC2N penetrates & fixes well into the leather fibres and therefore provides a longlasting softness.
- > Very Good light fastness
- **➢** Good softness
- Can be used for Pastal shades.

The above information on application on leather is given in accordance to the best of our knowledge and our lab applications. As the usage of the product by the consumer is not under our control, we are not liable for any sort of claims or reimbursements. The product is given without any guarantee/warranty in connection to end use.



## ZSIVIRA

### **ZSIVIROL IC2N**

### **Usage Quantities:**

Garment leather sheep Upto 6% ZSIVIROL IC2N

With 2 to 3% % ZSIVIROL LNM

Glove leather: 6.0% ZSIVIROL LNM, run 30 min.

6.0% ZSIVIROL IC2N

Garment Suedes: 2% to 3% ZSIVIROL LNM

4 % to 5%ZSIVIROL IC2N

Note: The product being combination of various raw materials, there are Chances of variations in colour and viscosity. The property and Application of the product will remain same.

The above information on application on leather is given in accordance to the best of our knowledge and our lab applications. As the usage of the product by the consumer is not under our control, we are not liable for any sort of claims or reimbursements. The product is given without any guarantee/warranty in connection to end use.