



Smart Chemistry

ZSIVIRA

ZSIVITAN MA30

Maleic Acrylic Copolymer

<i>Chemical composition</i>	<i>Maleic –Acrylic copolymer</i>
<i>Solids</i>	<i>30%</i>
<i>Appearance</i>	<i>Clear to Pale liquid</i>
<i>pH - value 1 : 10</i>	<i>5.5 – 6.5</i>
<i>Charge</i>	<i>anionic</i>
<i>Shelf life</i>	<i>Up to 1 year at temperatures between 5 and 40° C.</i>
<i>Dilution</i>	<i>Added Undiluted</i>

Field of application :

In the retanning of chrome and semi-chrome tanned leather.

Properties :

- *Gives a very fine and tight grain when used before neutralization..*
- *When used after neutralization it provides leather with excellent dry drumable property thereby producing even break.*
- *Allows an even dyeing with good light fastness*

Application:

ZSIVITAN MA can be applied alone or along with vegetable and other synthetic tannins.

In the Shoe Upper: 2 % to 6 % ZSIVITAN MA30

Upholstery leather: 2% to 6% ZSIVITAN MA30

Bovine garment leather: 2% to 3% ZSIVITAN MA30

Sheep Garment : 3% to 4% ZSIVITAN MA30

The above information on application on leather is given in accordance to the best of our knowledge and our lab applications. As the usage of the product by the consumer is not under our control, we are not liable for any sort of claims or reimbursements. The product is given without any guarantee/warranty in connection to end use.

ZSIVIRA CHEMIE MERK PRIVATE LIMITED

www.zsiviraindia.com info@zsiviraindia.com