



BASYPOL 115

Chrome Basifying Agent

Chemical composition	Blend of Organic and Inorganic compounds
Activity	98%
Appearance	Pale Pinkish White powder
Solubility	Sparingly soluble in weak acid solutions
Shelf life	Up to 6 months from the date of manufacture
Dilution	Added Undiluted

Field of application:

For the basification of chrome in chrome tanning.

Properties:

- » BASYPOL 115 being blend of special Inorganic compounds is an effective basifying agent .
- » BASYPOL 115 provides Wet Blue with uniform pleasant colour.
- » Avoids lot to lot variation of colour.
- » Provides smooth tight grain.
- » BASYPOL 115 provides maximum exhaustion and basification of chrome.
- » BASYPOL 115 increases the pH of the bath gradually and consistantly as the product is manufactured in such a way that it makes sustained rate of release of its compound when used.
- » BASYPOL 115 eliminates the chances of looseness and avoids over basification.

Application:

BASYPOL 115 is applied after through and through penetration of chrome and after the running time of Basic Chromium Sulfate.

BASYPOL 115 is added undiluted.

Usage:

Depending upon end pickle pH requirement a dosage of 0.3% to 0.5% will be enough.

To achieve pH 4.0 it is advised to run 5 to 6 hours.

As Basypol 115 absorbs moisture from air, it has to be stored in moisture free closed place.

Note : The product being combination of various raw materials, there are chances of variations in colour and viscosity. The property and application of the product will remain same.

Store within 5°C to 35°C in original pack with tightly closed.

The above information on application on leather is given in accordance to the best of our knowledge and our lab applications. As the usage of the product by the consumer is not under our control, we are not liable for any sort of claims or reimbursements. The product is given without any guarantee/warranty in connection to end use.

ZSIVIRA CHEMIE MERK PRIVATE LIMITED

www.zsiviraindia.com | info@zsiviraindia.com