



ZSIVIRA

ZSIVIROL FL506

Polyoxyethylene Based Fatliquor

Chemical composition	Blend of Synthetic Oils with Polyoxyethylene Ethers
Fattening substance	55 %
Appearance	Off White to Pale Beige Fluid
pH - value 1 : 10	5.5 – 7.0
Charge	Anionic
Stability to electrolytes	Stable to acids and salts under usual tannery conditions. Not stable in chrome liquors
Shelf life	Up to 1 year at temperatures between 5 and 40° C.
Dilution	Combinations with other fatliquors have to be stirred thoroughly before dilution. Dilution method: 1 : 3 with water of 50 – 60° C.

Field of application:

ZSIVIROL FL 506 is mainly used for high quality leather as shoe upper, goods, gloving and garment in the main fatliquoring bath. Fatliquor for soft, lightfast and odourless leathers.

Properties and Application:

- » Having Polyoxyethylene ethers bridged with synthetic oils ZSIVIROL FL506 penetrates & fixes well into the leather fibres and therefore provides a long-lasting softness.
- » Very Good light fastness.
- » Softness with roundness.
- » Best for white and pastel shades and wet white leathers.
- » Provides good body with filling on loose portions.

Usage Quantities:

Garment leather sheep	: Upto 5% ZSIVIROL FL506
Glove leather	: 3% ZSIVIROL FL 506
Garment Suedes	: 2 % – 4 % ZSIVIROL FL 506
Uppers	: Upto 5% ZSIVIROL FL506

Note : The product being combination of various raw materials, there are chances of variations in colour and viscosity. The property and application of the product will remain same.
Store within 5°C to 35°C in original pack with tightly closed.

The above information on application on leather is given in accordance to the best of our knowledge and our lab applications. As the usage of the product by the consumer is not under our control, we are not liable for any sort of claims or reimbursements. The product is given without any guarantee/warranty in connection to end use.

ZSIVIRA CHEMIE MERK PRIVATE LIMITED

www.zsiviraindia.com | info@zsiviraindia.com