



BISFREE TAN WJ

Hydrolysed and Polymers Tannins

| | |
|----------------------|--|
| Chemical composition | Tannin Condensate |
| Solids | 45 ± 2 % |
| Appearance | Opaque Liquid |
| pH - value 1 : 10 | 5.0 – 6.0 |
| Charge | Anionic |
| Shelf life | Up to 10 months from the date of manufacture |
| Dilution | Added Undiluted |

Field of application :

Re-tanning of chrome tanned and semi-chrome leathers.

Properties :

- » Free of Bisphenols and Formaldehyde
- » Fills the loose parts of the leather
- » Provides tightness and firmness
- » Good Light fastness.
- » Produce tight leather with a full handle and firm grain.

Usage Quantities:

Full grain upper leather : upto 6 %
Corrected grain upper leather : upto 5%
Garment leathers : upto 4 %

*Note : The product being combination of various raw materials, there are chances of variations in colour and viscosity. The property and application of the product will remain same.
Store within 5°C to 35°C in original pack with tightly closed.*

The above information on application on leather is given in accordance to the best of our knowledge and our lab applications. As the usage of the product by the consumer is not under our control, we are not liable for any sort of claims or reimbursements. The product is given without any guarantee/warranty in connection to end use.

ZSIVIRA CHEMIE MERK PRIVATE LIMITED

www.zsiviraindia.com | info@zsiviraindia.com