



ZSIVIRA

BISFREE TAN XJL

Bisphenol & Formaldehyde free Compact Tanning

Chemical composition	Organic and Natural Polycondensate
Active matter	45 ± 2 %
Appearance	Light Beige viscous Fluid
pH - value 1:10	5.0 – 5.5
Charge	Anionic
Light Fastness	Good
Stability to electrolytes	Stable to acids and salts under usual tannery conditions.
Shelf life	Up to 1 year at temperatures between 5 and 40° C.

Properties:

- » BISFREE TAN XJL is a compact tanning system which replaces most regular fatliquors and syntans usage.
- » Free from Formaldehyde and Bisphenols.
- » Best for White and Pastel shade dyeing.
- » Thoroughly fills up the loose portion entirely without affecting the softness.
- » Produces uniform clear grain with bouncy character and has excellent light fastness.
- » Best for Garment, shoe upper, Lining, Cow Nappa and Upholstery leathers.

Usage (on wetblue weight):

Sheep Garment (wet blue to crust)	: 10 - 14%
Sheep Shoe Nappa (wet blue to crust)	: 12 - 15%
Sheep Lining (wet blue to crust)	: 10 - 14%
Cow Nappa (wet blue to crust)	: 18 - 22%
Cow Softy (wet blue to crust)	: 18 - 25%

Note: The product being combination of various raw materials, there are chances of variations in colour and viscosity. The property and application of the product will remain same.

Store within 5°C to 35°C in original pack with tightly closed.

The above information on application on leather is given in accordance to the best of our knowledge and our lab applications. As the usage of the product by the consumer is not under our control, we are not liable for any sort of claims or reimbursements. The product is given without any guarantee/warranty in connection to end use.

ZSIVIRA CHEMIE MERK PRIVATE LIMITED

www.zsiviraindia.com | info@zsiviraindia.com