

## ZSIVITAN MA

### Maleic Acrylic Copolymer

Chemical composition	Maleic –Acrylic copolymer
Solids	30%
Appearance	Clear to Pale liquid
pH - value 1 : 10	5.5 – 6.5
Charge	Anionic
Shelf life	Up to 1 year at temperatures between 5 and 40° C.
Dilution	Added Undiluted

#### **Field of application :**

In the retanning of chrome and semi-chrome tanned leather.

#### **Properties :**

- » Gives a very fine and tight grain when used before neutralization..
- » When used after neutralization it provides leather with excellent dry drumable property thereby producing even break.
- » Allows an even dyeing with good light fastness

#### **Application:**

ZSIVITAN MA can be applied alone or along with vegetable and other synthetic tannins.

In the Shoe Upper	: 2% - 6 % ZSIVITAN MA
Upholstery leather	: 2% - 6% ZSIVITAN MA
Bovine garment leather	: 2% - 3% ZSIVITAN MA
Sheep Garment	: 3% - 4% ZSIVITAN MA

**Note :** The product being combination of various raw materials, there are chances of variations in colour and viscosity. The property and application of the product will remain same.  
Store within 5°C to 35°C in original pack with tightly closed.

The above information on application on leather is given in accordance to the best of our knowledge and our lab applications. As the usage of the product by the consumer is not under our control, we are not liable for any sort of claims or reimbursements. The product is given without any guarantee/warranty in connection to end use.

## ZSIVIRA CHEMIE MERK PRIVATE LIMITED

www.zsiviraindia.com | info@zsiviraindia.com