



ZSIVITAN RE

Acrylic Polymer with dispersants

Chemical composition	Blend of Poly acrylates
Solids	35 to 38%
Appearance	Amber viscous liquid. May turn little Reddish yellow upon storage in long term
pH - value 1 : 10	6.0 – 7.0
Charge	Anionic
Shelf life	Up to 10 months from the date of manufacture
Dilution	Added Undiluted

Field of application :

Anionic retanning agent for all kinds of leather chrome tanned, semi-chrome and full vegetable leather.

Properties :

- » ZSIVITAN RE is suitable for filling and tightening all types of chrome leathers without grain harshness.
- » Allow even dyeing with brilliant shades.

Usage Quantities:

In the Softy & upper leather : 3 – 5% ZSIVITAN RE
Garment leather : 3 – 4% ZSIVITAN RE

Note : The product being combination of various raw materials, there are chances of variations in colour and viscosity. The property and application of the product will remain same.
Store within 5°C to 35°C in original pack with tightly closed.

The above information on application on leather is given in accordance to the best of our knowledge and our lab applications. As the usage of the product by the consumer is not under our control, we are not liable for any sort of claims or reimbursements. The product is given without any guarantee/warranty in connection to end use.

ZSIVIRA CHEMIE MERK PRIVATE LIMITED

www.zsiviraindia.com | info@zsiviraindia.com