



# ZSIVIRA

## ZSIVITAN AL2

### Aluminium Syntan

Chemical composition	Cationic Aluminium Salts
Aluminium Oxide content	24 ± 1%
Basicity	50 – 55%
pH - value 1 : 10	2.5 ± 1
Charge	Cationic
Appearance	Pale White Granules
Shelf life	Up to 10 months from the date of manufacture
Dilution	Added to drum directly

#### **Field of application :**

In the wet white tanning, chrome free tanning and chrome retanning, in the EI / Vegetable tanning , solo aluminium and semi aluminium tanning.

#### **Properties**

- » ZSIVITAN AL2 provides soft, smooth leather with tight and firm grain.
- » ZSIVITAN AL2 has good filling effect.
- » ZSIVITAN AL2 does not harshen the grain layer.
- » ZSIVITAN AL2 due to its cationic action makes dyesuffs penetrate well into the leather and also makes dyeing surface evenly dyed with high light fastness.

#### **Usage Quantity :**

In the Tanning (after Chrome tanning) : 1 - 2.5% ( on pelt weight)  
In Goatskin Suede, Nubuck and Shoe Upper : 2 - 5%  
Retanning of Vegetable tanned leather EI sheep and goat skins : 5 - 8%

**Note :** The product being combination of various raw materials, there are chances of variations in colour and viscosity. The property and application of the product will remain same.  
Store within 5°C to 35°C in original pack with tightly closed.

The above information on application on leather is given in accordance to the best of our knowledge and our lab applications. As the usage of the product by the consumer is not under our control, we are not liable for any sort of claims or reimbursements. The product is given without any guarantee/warranty in connection to end use.

## ZSIVIRA CHEMIE MERK PRIVATE LIMITED

www.zsiviraindia.com | info@zsiviraindia.com