



ZSIVIRA

ZSIVITAN M

Dicyandiamide Condensation Syntan

Chemical composition	Dicyandiamide condensation product
Solids	97 %
Appearance	Pale White powder
pH - value 1 : 10	7.0 – 8.5
Charge	Anionic
Shelf life	Up to 1 year at temperatures between 5 and 40° C.
Dilution	Added Undiluted

Field of application :

Re-tanning and filling of chrome tanned and semi-chrome leathers.

Properties :

- » Fills the loose parts of the leather like shoulder, belly & flanks.
- » Provides even fullness throughout the leather.
- » Good Light fastness.
- » Produce soft leather with a full handle and firm grain.
- » Improves buffing properties.

Usage Quantities:

Full grain upper leather	: 3 – 5 % ZSIVITAN M
Corrected grain upper leather	: 2 – 5% ZSIVITAN M
Split Suedes	: 2 – 4 % ZSIVITAN M
Upholstery	: 2 – 4% ZSIVITAN M

Note : The product being combination of various raw materials, there are chances of variations in colour and viscosity. The property and application of the product will remain same.
Store within 5°C to 35°C in original pack with tightly closed.

The above information on application on leather is given in accordance to the best of our knowledge and our lab applications. As the usage of the product by the consumer is not under our control, we are not liable for any sort of claims or reimbursements. The product is given without any guarantee/warranty in connection to end use.

ZSIVIRA CHEMIE MERK PRIVATE LIMITED

www.zsiviraindia.com | info@zsiviraindia.com