



ZSIVIRA

ZSIVITAN DCD

Dicyandiamide Syntan

Chemical composition	Dicyandiamide condensation product
Activity	ca. 95 %
Appearance	Pale Tan to Off white powder
pH - value 1 : 10	7.0 – 9.0
Charge	Anionic
Shelf life	Up to 10 months from the date of manufacture
Dilution	Added Undiluted

Field of application:

Re-tanning and filling of all types of chrome leather where body and tightness is most needed. Contains Free Formaldehyde

Properties :

- » Specially fills the loose parts of the leather like shoulder, belly & flanks.
- » Provides even fullness throughout the leather.
- » Good Light fastness.
- » Produce soft leather with a full handle and firm grain.
- » Improves buffing properties.
- » Contains very less formaldehyde than conventional Dicyandiamide syntans.

Usage Quantities:

Full grain upper leather	: 3 – 5 % ZSIVITAN DCD
Corrected grain upper leather	: 2 – 5% ZSIVITAN DCD
Split Suedes	: 2 – 4 % ZSIVITAN DCD
Upholstery	: 2 – 4% ZSIVITAN DCD

Note : The product being combination of various raw materials, there are chances of variations in colour and viscosity. The property and application of the product will remain same.
Store within 5°C to 35°C in original pack with tightly closed.

The above information on application on leather is given in accordance to the best of our knowledge and our lab applications. As the usage of the product by the consumer is not under our control, we are not liable for any sort of claims or reimbursements. The product is given without any guarantee/warranty in connection to end use.

ZSIVIRA CHEMIE MERK PRIVATE LIMITED

www.zsiviraindia.com | info@zsiviraindia.com