



ZSIVIRA

ZSIVIROL 400

Sulfited Fish Oil

Chemical composition	Less odour sulfited fish oil with synthetic oils and emulsifiers
Solids	60 %± 2%
Appearance	Reddish Brown oil
pH - value 1 : 10	6.0 – 7.0
Charge	Anionic
In Stability to electrolytes	Stable to acids and salts under usual tannery conditions. Stable to Chrome
Shelf life	Upto 10 months from date of manufacture
Dilution	Combinations with other fatliquors have to be stirred thoroughly before dilution. Dilution method: 1 : 3 with water of 50 – 60° C.

Field of application:

Fatliquor for soft garment , goods and upholstery leathers

Properties and Application:

- » Provides leather with good softness and soft touch.
- » Provides excellent inner softness.
- » Good Light Fastness.
- » Compatible with other fatliquors.
- » Can be used in chrome tanning , retanning and main fatliquoring.

Usage Quantities:

In chrome tanning : 0.5 – 2.0% ZSIVIROL 400
In chrome retanning : 1.0 – 2.0% ZSIVIROL 400
In main fatliquor for garment
Goods & upholstery leathers : 3.0 – 8.0% ZSIVIROL 400

Note : The product being combination of various raw materials, there are chances of variations in colour and viscosity. The property and application of the product will remain same.
Store within 5°C to 35°C in original pack with tightly closed.

The above information on application on leather is given in accordance to the best of our knowledge and our lab applications. As the usage of the product by the consumer is not under our control, we are not liable for any sort of claims or reimbursements. The product is given without any guarantee/warranty in connection to end use.

ZSIVIRA CHEMIE MERK PRIVATE LIMITED

www.zsiviraindia.com | info@zsiviraindia.com