



# **BISFREE TAN SWL liq**

## **Liquid Sulfone Condensate**

Chemical composition	Liquid Sulfone Condensate free of Bisphenols and Free Formaldehyde
Solids	44 ± 3%
Appearance	Pale Yellow Liquid (Turns Reddish on Ageing)
pH - value 1:10	2.0 - 4.0
Charge	Anionic
Shelf life	Up to 10 months from the date of manufacture
Dilution	Added Undiluted

### Field of application:

In production of chrome and chrome free leathers where fullness, tightness with brilliancy is needed.

#### **Properties:**

- BISFREE TAN SWL LIq is free From BISPNENOL A,F and AF and Formaldehyde contains small form of BISPHENOL S, which will not be found in leather after application.
- » BISFREE TAN SWL liq gives leather very good fastness and a smooth and fine grain with specific filling in loose areas.
- » Exhibits excellent light fastness and heat migration fastness and hence suitable for pastel shade dyeing.
- » Can be used as a single syntan for white leathers and provides Brilliant shade in pastal colour dyeing.
- » Reduces defects visibility.
- » In vegetable tanning it improves the colour and light fastness and better dispersion of veg tans.
- » Suitable for chrome and vegetable tanning and retanning.

## **Usage Quantities:**

Pre-Tanning : 3 - 6% Retanning : 3 - 5%

In Rechroming along with chrome : 3 - 4% (after reducing pH)

Note: The product being combination of various raw materials, there are chances of variations in colour and viscosity. The property and application of the product will remain same. Store within 5°C to 35°C in original pack with tightly closed.

The above information on application on leather is given in accordance to the best of our knowledge and our lab applications. As the usage of the product by the consumer is not under our control, we are not liable for any sort of claims or reimbursements. The product is given without any guarantee/warranty in connection to end use.

ZSIVIRA CHEMIE MERK PRIVATE UMITED