



BISFREE TAN ZPS

Cross Condensated Polymer Tannins

Chemical composition	Synthetic Polymer Condensate
Solids	98± 2 %
Appearance	Pale Beige powder
pH - value 1 : 10	5.0 – 7.0
Charge	Anionic
Shelf life	Up to 10 months from the date of manufacture
Dilution	Added Undiluted

Field of application :

Re-tanning of chrome tanned and semi-chrome leathers.

Properties :

- » Free of Bisphenols and Formaldehyde.
- » Fills the loose parts of the leather.
- » Improves the buffing properties.
- » Good Light fastness.
- » Produce soft leather with a full handle and firm grain.

Usage Quantities:

Full grain upper leather	: upto 6 %
Corrected grain upper leather	: upto 6%
Garment leathers	: upto 6 %
Suede crusting	: upto 5%

Note : The product being combination of various raw materials, there are chances of variations in colour and viscosity. The property and application of the product will remain same.

Store within 5°C to 35°C in original pack with tightly closed.

The above information on application on leather is given in accordance to the best of our knowledge and our lab applications. As the usage of the product by the consumer is not under our control, we are not liable for any sort of claims or reimbursements. The product is given without any guarantee/warranty in connection to end use.

ZSIVIRA CHEMIE MERK PRIVATE LIMITED

www.zsiviraindia.com | info@zsiviraindia.com