



# **ZSIVITAN RW Liq**

### **Polycondensated Phenolic Sulfone**

Chemical composition	Phenolic Sulfone Polycondensate
Solids	40% to 45%
Appearance	Reddish Liquid
pH - value 1:10	3.0 - 4.0
Charge	Anionic
Shelf life	Up to 10 months from the date of manufacture
Dilution	Added Undiluted

## Field of application:

In all type of leathers where fullness with clean dyeing is needed.

### **Properties:**

- » Gives leather fullness and a fine grain with good filling.
- » Can be used in retanning and chrome tanned and veg tanned leathers.
- » Makes light colour dyeing possible with even dyeing and brilliant shades both in chrome tanned and veg tanned leathers.
- » Produces Leather with light weight.
- » Avoids looseness.

## **Usage Quantities:**

In Upper leather : Upto 6 %
For Drum dyed articles : Upto 8%
EI Pretanning : Upto 4%
Garment Leathers : Upto 6%

Note: The product being combination of various raw materials, there are chances of variations in colour and viscosity. The property and application of the product will remain same.

Store within 5°C to 35°C in original pack with tightly closed.

The above information on application on leather is given in accordance to the best of our knowledge and our lab applications. As the usage of the product by the consumer is not under our control, we are not liable for any sort of claims or reimbursements. The product is given without any guarantee/warranty in connection to end use.

ZSIVIRA CHEMIE MERK PRIVATE UMITED