



ZSIVITAN MHPS

Cross Condensated Melamine Syntan

Chemical composition	Melamine Cross Condensated with Biopolymers
Solids	99 %
Appearance	Pale Beige powder
pH - value 1:10	6.5 – 7.5
Charge	Anionic
Shelf life	Up to 10 months from the date of manufacture
Dilution	Added Undiluted

Field of application:

Re-tanning and filling of chrome tanned and semi-chrome leathers

Properties:

- · Fills the loose parts of the leather
- · Improves the buffing properties

without any guarantee/warranty in connection to end use.

- Good Light fastness.
- Produce soft leather with a full handle and firm grain.

Usage Quantities:

Full grain upper leather : 3 to 5 % ZSIVITAN MHPS
Corrected grain upper leather : upto 6% ZSIVITAN MHPS
Garment leathers : 3 to 5 % ZSIVITAN MHPS
Suede crusting : 2 to 4% ZSIVITAN MHPS

Note: The product being combination of various raw materials, there are chances of variations in colour and viscosity. The property and application of the product will remain same.

Store within 5°C to 35°C in original pack with tightly closed.

The above information on application on leather is given in accordance to the best of our knowledge and our lab applications. As the usage of the product by the consumer is not under our control, we are not liable for any sort of claims or reimbursements. The product is given

ZSIVIRA CHEMIE MERK PRIVATE UMITED