

# ZSIVIRA

# **ZSIVITAN ACR**

Acrylic Polymer

Chemical composition	High molecular weight synthetic organic resin tanning agent based on water soluble acrylic polymer
Solids	30 to 35%%
Appearance	Clear viscous liquid. May turn little yellow upon improper storage in long term
pH - value 1:10	6.0-7.5
Charge	Anionic
Shelf life	Up to 1 year at temperatures between 5 and 40° C.
Dilution	Added Undiluted

## Field of application:

Anionic retanning agent for all kinds of leather chrome tanned, semi-chrome and full vegetable leather.

### Properties:

- > ZSIVITAN ACR is suitable for filling and tightening all types of chrome leathers without grain harshness
- > Allow even dyeing with brilliant shades.

### Usage Quantities:

In the Softy & upper leather: 2 to 4 % ZSIVITAN ACR

garment leather: 2 to 5% ZSIVITAN ACR

Note: The product being combination of various raw materials, there are chances of variations in colour and viscosity. The property and Application of the product will remain same.

The above information on application on leather is given in accordance to the best of our knowledge and our lab applications. As the usage of the product by the consumer is not under our control, we are not liable for any sort of claims or reimbursements. The product is given without any guarantee/warranty in connection to end use.