

ZSIVIRA

ZSIVITAN AN

Amphoteric Syntan

Chemical composition	Aromatic Phenol Condensation Product
Solids	96 %
Appearance	Creamish powder
pH - value 1:10	3.5 - 4.5
Charge	Amphoteric
Shelf life	Up to 1 year at temperatures between 5 and 40° C.
Dilution	Added Undiluted

Field of application:

Re-tanning and filling of all types of chrome and semi-chrome leathers.

Properties:

- > ZSIVITAN AN being amphoteric special syntan can be used in all stages of rechroming and retanning.
- > ZSIVITAN AN produces leathers of light weight, smooth grain with soft feel.
- > ZSIVITAN AN is best for production of smooth nappa, nubuck and suedes.
- > ZSIVITAN AN enhances the filling action of vegetable extracts.
- > ZSIVITAN AN provides uniform dyeability both on grain and flesh side and improves dye intensity to the leather.

The above information on application on leather is given in accordance to the best of our knowledge and our lab applications. As the usage of the product by the consumer is not under our control, we are not liable for any sort of claims or reimbursements. The product is given without any guarantee/warranty in connection to end use.





ZSIVITAN AN

Amphoteric Syntan

Usage Quantities:

Cow nappa: 2 to 3 % ZSIVITAN AN

Sheep nappa: 3 to 4% ZSIVITAN AN

Nubuck: 3 to 4 % ZSIVITAN AN

Note: The product being combination of various raw materials, there are chances of variations in colour. The property and Application of the product will remain same.

The above information on application on leather is given in accordance to the best of our knowledge and our lab applications. As the usage of the product by the consumer is not under our control, we are not liable for any sort of claims or reimbursements. The product is given without any guarantee/warranty in connection to end use.