

# ZSIVIRA

## **ZSIVITAN RW Liq**

Polymerised Phenolic Sulfone

Chemical composition	Phenolic Sulfone Condensated with Polymer
Solids	40% to 45%
Appearance	Reddish Liquid
pH - value 1:10	3.0-4.0
Charge	Anionic
Shelf life	Up to 1 year at temperatures between 5 and 40° C.
Dilution	Added Undiluted

### Field of application:

In all type of leathers where fullness with clean dyeing is needed.

### **Properties:**

- > Gives leather fullness and a fine grain with good filling.
- Can be used in retanning and chrome tanned and veg tanned leathers.
- > Makes light colour dyeing possible with even dyeing and brilliant shades both in chrome tanned and veg tanned leathers.
- > Produces Leather with light weight.
- > Avoids looseness.

The above information on application on leather is given in accordance to the best of our knowledge and our lab applications. As the usage of the product by the consumer is not under our control, we are not liable for any sort of claims or reimbursements. The product is given without any guarantee/warranty in connection to end use.



## ZSIVIRA

### **ZSIVITAN RW Liq**

Polymerised Phenolic Sulfone

### **Usage Quantities:**

In Upper leather: Upto 6 %

For Drum dyed articles: Upto 8%

EI Pretanning: Up to 4%

Garment Leathers: Upto 6%

Shoe Nappa: Upto 7%

Note: The product being combination of various raw materials, there are chances of variations in colour. The property and Application of the product will remain same.

The above information on application on leather is given in accordance to the best of our knowledge and our lab applications. As the usage of the product by the consumer is not under our control, we are not liable for any sort of claims or reimbursements. The product is given without any guarantee/warranty in connection to end use.

#### ZSIVIRA CHEMIE MERK PRIVATE LIMITED